

أرامكو دورا®

الفحص	الوحدة	الطريقة	أرامكو دورا 150BS
		Typical	أولسان
Appearance		Visual	C & B
Kinematic Viscosity @ 40°C	cSt	ASTM D445	488.6
Kinematic Viscosity @ 100°C	cSt	ASTM D445	31.85
Viscosity Index		ASTM D2270	96
Sulfur Content	ppm	ASTM D5453	<100
Pour Point	°C	ASTM D5950/6749	-14
Density @ 15.6 °C	kg/L	ASTM D1298	0.8929
Color, ASTM		ASTM D1500	L 1.0
Flash Point, COC	°C	ASTM D92	316
Flash Point, PMCC	°C	ASTM D93	
Furfural Content	ppm	M-1414	
Copper Strip Corrosion, 100°C, 3 hrs		ASTM D130	1b
Conradson Carbon Residue	wt%	ASTM D4530	0.2
Total Acid Number	mgKOH/g	ASTM D974	<0.01