

أرامكو بريما

بورت أرثر

Port Arthur

الفحص	الوحدة	الطريقة	220	بريما 100
المجموعة II				
Group II				Typical
Appearance		Visual		C&B
Kinematic Viscosity @ 40°C	cSt	D 445		42.3
Kinematic Viscosity @ 100°C	cSt	D 445		6.5
Viscosity Index		D 2270		104
Saturates	wt%	D 2007		
Sulfur	wt ppm	D 2622		<10
Noack Volatility (Procedure B)	wt%	D 5800		11.0
CCS Viscosity @ -20°C	mPa-s	D 5293		3,080
Pour Point	°C	D 5950		-15
Density @ 15°C	kg/L	D 4052		0.8640
Saybolt Color		D 156		
ASTM Color	ASTM	D 1500		L 0.5
Flash Point COC	°C	D 92		226
Copper Corrosion 100°C 3hrs				
Total Acid Number	mgKOH/gm	D 974		
Aromatics	wt%	D 2007		
Aniline Point	°C	D 611		