



أرامكو بريما

ARAMCO PRIMA

الفحص	الوحدة	الطريقة	500 بريما 60	المجموعة II
Group II				أولسان
Appearance		Visual	C & B	
Kinematic Viscosity @ 40°C	cSt	D 445	96.4	
Kinematic Viscosity @ 100°C	cSt	D 445	11.3	
Viscosity Index		D 2270	104	
Saturates	wt%	D 2007	99	
Sulfur	wt ppm	D 5453	2 [‡]	
Noack Volatility (Procedure B)	wt%	D 5800	6.9	
CCS Viscosity @ -20°C	mPa-s	D 5293	14,550	
CCS Viscosity @ -25°C	mPa-s	D 5293	26,000	
Pour Point	°C	D 97	-18	
Brookfield @ -40°C		D 2983		
Density @ 15°C	Kg/L	D 4052	0.8720	
Saybolt Color	°C	D 156	+30	
ASTM Color	°C	D 1500	L0.5	
Flash Point COC	°C	D 92	240	
Copper Corrosion 100°C 3hrs		D 130	1b	
Total Acid Number	mgKOH/gm wt%	D 974	< 0.01	
Aromatics		D 2007	< 1	

Notes: [‡] - D 2622