



# aramcoULTRA<sup>®</sup>

Test	Unit	Method	aramcoULTRA <sup>®</sup> 6
		Typical	Ulsan
Appearance		Visual	C&B
Kinematic Viscosity @ 40°C		D 445	32.54
Kinematic Viscosity @ 100°C		D 445	6.04
Viscosity Index		D 2270	134
Saturates	wt%	D 2007	>99
Sulfur	wt ppm	D2622	<1.0
Noack Volatility	wt% (Procedure B)	D 5800	6.4
CCS Viscosity @ -30°C	mPa-s	D 5293	3,850
Pour Point	°C	D 97	-16
Density @ 15°C	Kg/L	D 4052	0.8398
Saybolt Color		D 156	+30
Color	ASTM	D 1500	L0.5
Flash Point COC	°C	D 92	240
Copper Corrosion 100°C 3hrs		D 130	1b
Total Acid Number	mgKOH/gm	D 974	L0.01
Aromatics	wt%	D 2007	<1