



aramcoULTRA®

Test	Unit	Method	aramcoULTRA® 4
		Typical	Ulsan
Appearance		Visual	C&B
Kinematic Viscosity @ 40°C		D 445	19.7
Kinematic Viscosity @ 100°C		D 445	4.27
Viscosity Index		D 2270	124
Saturates	wt%	D 2007	>99
Sulfur	wt ppm	D2622	1
Noack Volatility (Procedure B)	wt% (Procedure B)	D 5800	14.7
CCS Viscosity @ -30°C Pour	mPa-s	D 5293	1,500
Point	°C	D 97	-20
Density @ 15°C	kg/L	D 4052	0.8350
Saybolt Color		D 156	+30
ASTM Color	ASTM	D 1500	L0.5
Flash Point COC	°C	D 92	220
Copper Corrosion 100°C 3hrs		D 130	1b
Total Acid Number	mgKOH/gm	D 974	L0.01
Aromatics	wt%	D 2007	<1